

2.708.080X

SELEMIX 1K ГРУНТ

2.708.0800 СЕРЫЙ
2.708.0801 КРАСНЫЙ

ОПИСАНИЕ МАТЕРИАЛА

2.708.08xx - серия Selemix 1K антикоррозионных синтетических грунтов с превосходной адгезией с голой сталью. Данные продукты рекомендованы для окрашивания компонентов сельскохозяйственной и строительной техники, а также других изделий из металла.







ВЫБОР И ПОДГОТОВКА СУБСТРАТА




Сталь Дробеструй
P80-120 -240(сухое)

Перед нанесение поверхность должна быть тщательно обезжирена

РУКОВОДСТВО ПО ПРИМЕНЕНИЮ

Пропрции смешивание (по весу)	БЕЗВОЗДУШНОЕ/ КОМБИНИРОВАННОЕ		СТАНДАРТНОЕ	
	Грунт	1000	Грунт 1-610*	1000 0-5%
			*1-215 или 1-205	0-5%
 Срок годности 20°C	Без ограничений		Без ограничений	
 Вязкость	35-40 с Din 4 при 20°C		20-25 с Din 4 при 20°C	
 Сопло	9 – 11		1.4-1.7 мм	
 Давление	120-140 бар – Безвоздушное 70 – 100 бар – Комбинированное		3-4 бар	
 Число слоев	2		2	
 Выдержка между слоями	5-7 мин 20°C		5-7 мин 20°C	

РУКОВОДСТВО ПО ПРИМЕНЕНИЮ



Время сушки при 20°C:

От пыли:

10-15 мин

Монтажная прочность:

30-60 мин



Полное высыхание:

1 день

Толщина пленки:

50-60 мкм

Время перекрывания:

Мин. 1ч 20°C
Макс 1 месяц без
шлифования

Последующий материал:

Любые 1К или 2К Selemix
эмали (исключение
эпоксиды)

СВОЙСТВА ЛКМ И ПОКРЫТИЯ

Теоретическая укрывистость, м²/л

5,2-6,0 при 50 мкм

МЕРЫ ПРЕДОСТОРОЖНОСТИ

См. руководство по технике безопасности и маркировку материалов для получения полной информации о мерах предосторожности и технике безопасности.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

SELEMIX SYSTEM is a brand of PPG Group.

PPG Industries (UK) Ltd, Auto refinish, Customers Service and Sales Group, Needham Road, Stowmarket, Suffolk, IP14 2AD, England, Tel : 01449 771775, Fax : 01449 771547